

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
17 February 2005 (17.02.2005)

PCT

(10) International Publication Number  
**WO 2005/014882 A1**

- (51) International Patent Classification<sup>7</sup>: **C23C 28/00**, 16/26, 16/02
- (21) International Application Number: PCT/EP2004/051320
- (22) International Filing Date: 1 July 2004 (01.07.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 03102294.0 25 July 2003 (25.07.2003) EP
- (71) Applicant (for all designated States except US): NV Bekaert SA [BE/BE]; Bekaertstraat 2, B-8550 ZW-EVEGEM (BE).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): DENUL, Jürgen [BE/BE]; Krekelstraat 119, B-9800 DEINZE (BE). DEKEMPENEER, Erik [BE/BE]; Lochtiens 21, B-2390 OOSTMALLE (BE). DE BOSSCHER, Wilmert [BE/BE]; Noordhoutstraat 22, B-9031 DRONGEN (BE).
- (74) Agent: HEYDE, Katrien; Bekaertstraat 2, B-8550 ZW-EVEGEM (BE).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:  
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: SUBSTRATE COVERED WITH AN INTERMEDIATE COATING AND A HARD CARBON COATING

(57) Abstract: The invention relates to a substrate covered at least partially with a layered coating. The layered coating comprises an intermediate coating and a hard carbon coating. The intermediate coating comprises a first metal layer deposited on the substrate, the first metal layer comprising at least one element of group IVB, group VB or group VIB; a nitride layer deposited on the first metal layer, the nitride layer comprising at least one nitride of an element of group IVB, group VB or group VIB; a second metal layer deposited on the nitride layer, the second metal layer comprising at least one element of group IVB, group VB or group VIB; a transition layer deposited on the second metal layer, the transition layer comprising at least one carbide of an element of group IVB, group VB or group VIB.

WO 2005/014882 A1

WO 2005/014882

PCT/EP2004/051320

**Substrate covered with an intermediate coating and a hard carbon coating**

**Field of the invention.**

5 The invention relates to a substrate covered at least partially with an intermediate coating and a hard carbon coating.

**Background of the invention.**

10 Hard carbon coatings such as diamond-like carbon (DLC) coatings are attractive coatings for example because of their high hardness and low coefficient of friction, their chemical inertness and their biocompatibility. One of the main problems of DLC coatings is the poor adhesion to a substrate.

15 It has been found that the application of one or more intermediate layers between the DLC coating and the substrate can promote the adhesion strength. A variety of interlayers have been tested, such as an interlayer of Ti, TiN or TiC.

FR 2 596 775 describes the use of a TiN-TiCN intermediate layer. However, adhesion of DLC coatings to the substrate is still an issue.

20

**Summary of the invention.**

It is an object of the invention to provide a coating having an improved adhesion to a substrate.

25 According to a first aspect of the present invention a substrate covered at least partially with a layered coating is provided.

The layered coating comprises an intermediate coating and a hard carbon coating. The intermediate coating comprises :

- 30
- a first metal layer deposited on the substrate, the first metal layer comprising at least one element of group IVB, group VB or group VIB;
  - a nitride layer deposited on the first metal layer, the nitride layer comprising at least one nitride of an element of group IVB, group VB or group VIB;

WO 2005/014882

PCT/EP2004/051320

-2-

- a second metal layer deposited on the nitride layer, the second metal layer comprising at least one element of group IVB, group VB or group VIB;
- 5        - a transition layer deposited on the second metal layer, the transition layer comprising at least one carbide of an element of group IVB, group VB or group VIB.

The first and the second metal layers are adhesion promoting layers :

- 10       - The first metal layer, i.e. the layer situated between the substrate and the nitride layer, is promoting the adhesion of the nitride to the substrate.
- The second metal layer, i.e. the layer situated between the nitride and the carbide layer, is promoting the adhesion of the carbide layer to the nitride layer.

15

The hard carbon coating may comprise any carbon-based coating known in the art.

Preferably, the hard carbon coating comprises a diamond-like coating. Diamond-like coatings are amorphous carbon based coatings with a  
20       high hardness and a low coefficient of friction. Their unique composition and structure result in excellent wear resistance and non-sticking characteristics.

Diamond-like coatings comprise for example diamond-like carbon (DLC) coatings and diamond-like nanocomposite (DLN) coatings or layered  
25       structures of diamond-like carbon (DLC) and diamond-like nanocomposite (DLN) coatings.

Diamond-like carbon coatings comprise amorphous hydrogenated carbon coatings (a-C:H); whereas diamond-like nanocomposite coatings  
30       comprise interpenetrating networks of a-C:H and a-Si:O. A representative DLN coating comprises 30 to 70 at% of C, 20 to 40 at% of H, 5 to 15 at% of Si and 5 to 15 at% of O.

WO 2005/014882

PCT/EP2004/051320

-3-

DLN coating exhibits a very low coefficient of friction, even in high humidity or wet environment.

5 The hard carbon coating such as the diamond-like coating may be deposited by any technique known in the art. A preferred technique comprises chemical vapor deposition (CVD), such as plasma assisted chemical vapor deposition (PACVD).

10 To influence its conductivity, the hard carbon coating such as the DLC or DLN coating can further be doped with a transition metal. In particular W, Zr, Ti, Nb and Ta are well suited as doping elements.

The DLC or DLN coating can further contain an inert gas such as Ne, Ar or Kr, for example in an amount of 0.5 to 5 at%.

15 The first metal layer and the second metal layer may comprise any element or combination of elements of group IVB, group VB or group VIB. In preferred embodiments the first and/or the second metal layer comprise Ti or Cr.

20 The first metal layer and the second metal layer preferably have a thickness ranging between 0.001 and 1  $\mu\text{m}$ , for example between 0.001 and 0.1  $\mu\text{m}$ , such as 0.05  $\mu\text{m}$ .

25 The nitride layer may comprises at least one nitride of an element of group IVB, group VB or group VIB. In a preferred embodiment, the nitride layer comprises TiN or CrN.

The nitride layer is giving the layered coating in combination with the hard carbon coating the required mechanical properties.

30

WO 2005/014882

PCT/EP2004/051320

-4-

The thickness of the nitride layer is preferably between 0 and 5  $\mu\text{m}$ .  
More preferably, the nitride layer has a thickness between 0.001 and 1  $\mu\text{m}$ , for example 0.75 or 1  $\mu\text{m}$ .

- 5 The transition layer deposited on the second metal layer comprises at least one carbide of an element of group IVB, group VB or group VIB. The transition layer comprises preferably  $\text{Ti}_x\text{C}_y$  or  $\text{Cr}_x\text{C}_y$ . The transition layer comprises for example stoichiometric  $\text{TiC}$  or  $\text{Cr}_2\text{C}_3$ . However, the transition layer may also comprise non-stoichiometric  $\text{Ti}_x\text{C}_y$  or  $\text{Cr}_x\text{C}_y$ .
- 10 Preferably, the transition layer shows a gradient, whereby the carbon content is increasing and the metal content is decreasing from the side of the transition layer in contact with the second metal layer towards the side of the transition layer in contact with the hard carbon coating.
- 15 The thickness of the carbide layer is preferably between 0.001 and 1  $\mu\text{m}$ , for example 0.1  $\mu\text{m}$ .
- The layered coating according to the present advantage combines the characteristics of having a good adhesion to the substrate and having a high hardness.
- 20 The adhesion of the layered coating according to the invention, expressed by means of the Rockwell C indentation test is better than HF2 and more preferably equal to HF1 (VDI 3198 norm).
- 25 The critical load to obtain delamination in a scratch test (European Standard suggestion prEN 1071-3) is higher than 35 N and more preferably higher than 50 N.
- 30 The hardness of the layered coating according to the invention is higher than 10 GPa. In a preferred embodiment a hardness of at least 20 GPa has been reached. The hardness can be influenced by the choice of the top layer of the layered coating.

WO 2005/014882

PCT/EP2004/051320

-5-

5 The substrate to be coated may comprise any substrate, either flexible or rigid. Examples of substrates comprise steel substrates, hard metal cermets, silicon substrates, aluminium or aluminium alloy substrates, titanium or titanium alloy substrates, copper or copper alloy substrates, ceramics or glass substrates.

10 The layered coating according to the present invention can be used in a great number of applications. The composition of the DLC coating can be adjusted specifically to meet preset requirements such as low friction, high hardness, high abrasion and wear resistance, high corrosion resistance and non-sticking properties.

15 The layered coating according to the present invention can for example be used to coat all kinds of mouldings means, medical implants, automotive powertrain components, textile components, ...

**Description of the preferred embodiments of the invention.**

To evaluate the influence of the first metal layer, two samples are compared.

20 In a first sample a TiN layer is deposited directly on the substrate; in a second sample a Ti layer (0.010  $\mu\text{m}$ ) is deposited on the substrate and a TiN layer is deposited on the Ti layer.

25 In the first sample, the TiN layer delaminates immediately after removal from the substrate holder. Delamination was most dramatic at the edges of the sample. At these edges the ion bombardment during growth is more intense due to edge field effects. This can result in higher stresses in the coating which can cause the coating to delaminate more easily. Both indentation test (HF6) and scratch test (critical load = 16 N) confirm the poor adhesion.

30 The second sample shows good adhesion, confirmed both by the indentation test (HF1) and the scratch test (critical load > 30 N). In one embodiment a scratch test showed a critical load higher than 47 N.

WO 2005/014882

PCT/EP2004/051320

-6-

In order to check the need of a transition layer before the deposition of a hard carbon layer, such as a DLC layer, DLC was deposited directly on the TiN layer (0.01  $\mu\text{m}$  Ti / 0.6  $\mu\text{m}$  TiN / 1.3  $\mu\text{m}$  DLC).

5 Delamination of the DLC from the TiN could be observed. This poor adhesion was confirmed by a very bad indentation result and a low critical load value (28 N) in the scratch tests.

This result proves that the transition between the TiN and the DLC coating is critical and that a kind of transition layer is necessary.

Three different samples were compared :

- 10 1) a layered coating comprising  
0.1  $\mu\text{m}$  Ti / 0.6  $\mu\text{m}$  TiN / 0.6  $\mu\text{m}$  TiC / 1.3  $\mu\text{m}$  DLC;  
2) a layered coating comprising  
0.1  $\mu\text{m}$  Ti / 0.6  $\mu\text{m}$  TiN / 0.3  $\mu\text{m}$  TiNC / 1.3  $\mu\text{m}$  DLC;  
15 3) a layered coating comprising  
0.01  $\mu\text{m}$  Ti / 0.75  $\mu\text{m}$  TiN / 0.01  $\mu\text{m}$  Ti / 0.1  $\mu\text{m}$  TiC / 1.3  $\mu\text{m}$  DLC.

20 The first and second sample show a poor adhesion, whereas the third sample shows a good adhesion. The good adhesion of the third sample is confirmed by indentation tests (HF1) and scratch test (critical load > 40 N)

In another example the layered coating comprises an intermediate coating comprising :

- 25 - a first Cr layer;  
- a CrN layer;  
- a second Cr layer;  
- a  $\text{Cr}_x\text{Cy}$  layer, such as a  $\text{Cr}_3\text{C}_2$  layer.

WO 2005/014882

PCT/EP2004/051320

-7-

**CLAIMS**

1. A substrate covered at least partially with a layered coating, said layered coating comprising an intermediate coating and a hard carbon coating, characterised in that said intermediate coating comprises
- 5
- a first metal layer deposited on the substrate, said first metal layer comprising at least one element of group IVB, group VB or group VIB;
  - 10 - a nitride layer deposited on said first metal layer, said nitride layer comprising at least one nitride of an element of group IVB, group VB or group VIB;
  - a second metal layer deposited on said nitride layer, said second metal layer comprising at least one element of group IVB, group VB or group VIB;
  - 15 - a transition layer deposited on said second metal layer, said transition layer comprising at least one carbide of an element of group IVB, group VB or group VIB.
- 20
2. A substrate according to claim 1, whereby said hard carbon coating comprises a diamond-like carbon (DLC) coating.
3. A substrate according to claim 1, whereby said hard carbon coating comprises a diamond-like nanocomposite (DLN) coating.
- 25
4. A substrate according to claim 1, whereby said hard carbon coating comprises a layered structure of diamond-like carbon (DLC) and diamond-like nanocomposite (DLN) coatings.
- 30
5. A substrate according to any one of the preceding claims, whereby said hard carbon coating is doped with a transition metal and/or with an inert gas.



WO 2005/014882

PCT/EP2004/051320

-8-

6. A substrate according to any one of the preceding claims,  
whereby said first metal layer comprises Ti or Cr.
- 5 7. A substrate according to any one of the preceding claims,  
whereby said nitride layer comprises TiN or CrN.
8. A substrate according to any one of the preceding claims,  
whereby said second metal layer comprises Ti or Cr.
- 10 9. A substrate according to any one of the preceding claims,  
whereby said transition layer comprises  $Ti_xC_y$  or  $Cr_xC_y$ .
- 15 10. A substrate according to any one of the preceding claims,  
whereby said first metal layer and said second metal layer have  
a thickness between 0.001 and 1  $\mu m$ .
11. A substrate according to any one of the preceding claims,  
whereby said nitride layer has a thickness between 0 and 5  $\mu m$ .
- 20 12. A substrate according to any one of the preceding claims,  
whereby said transition layer has a thickness between 0.001 and  
1  $\mu m$ .
- 25 13. A substrate according to any one of the preceding claims,  
whereby the adhesion of said layered coating expressed by  
means of the Rockwell C test is better than HF2.
- 30 14. A substrate according to any one of the preceding claims,  
whereby the adhesion of said layered coating expressed by  
means of the critical load to obtain delamination is higher than 35  
N.
- 35 15. A substrate according to any one of the preceding claims,  
whereby said layered coating has a hardness of at least 10 GPa.

# INTERNATIONAL SEARCH REPORT

International Application No  
PCT/EP2004/051320

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 7 C23C28/00 C23C16/26 C23C16/02

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)  
IPC 7 C23C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, INSPEC

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 100 18 143 A (BALZERS HOCHVAKUUM) 25 October 2001 (2001-10-25)  page 3, paragraph 19-28 page 9, paragraph 95 - page 11, paragraph 110  -----	1,2,5,6, 8-10,12, 13,15
A	US 6 126 793 A (KOIKE RYOTA ET AL) 3 October 2000 (2000-10-03) column 6, lines 1-7,16-22 column 18, line 29 - column 19, line 34 column 20, lines 1-26 column 20, line 53 - column 21, line 16  ----- -/--	1,2,6, 8-10,12

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- \*A\* document defining the general state of the art which is not considered to be of particular relevance
- \*E\* earlier document but published on or after the international filing date
- \*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- \*O\* document referring to an oral disclosure, use, exhibition or other means
- \*P\* document published prior to the international filing date but later than the priority date claimed

- \*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- \*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- \*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- \*Z\* document member of the same patent family

Date of the actual completion of the international search

6 October 2004

Date of mailing of the international search report

15/10/2004

Name and mailing address of the ISA  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Joffreau, P-0

## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/EP2004/051320

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 6 033 533 A (KOIKE RYOTA ET AL) 7 March 2000 (2000-03-07) column 6, lines 1-7,16-23 column 18, line 29 - column 19, line 34 column 20, line 53 - column 21, line 16 -----	1,2,6, 8-10,12
A	HUANG R F ET AL: "Wear-resistant multilayered diamond-like carbon coating prepared by pulse biased arc ion plating" DIAMOND AND RELATED MATERIALS, ELSEVIER SCIENCE PUBLISHERS, AMSTERDAM, NL, vol. 10, no. 9-10, September 2001 (2001-09), pages 1850-1854, XP004321135 ISSN: 0925-9635 page 1851, paragraph 2 page 1852, paragraph 3; figure 3; table 1 -----	1,2,5-12
A	DENG J ET AL: "DLC multilayer coatings for wear protection" DIAMOND AND RELATED MATERIALS, ELSEVIER SCIENCE PUBLISHERS, AMSTERDAM, NL, vol. 4, no. 7, 15 May 1995 (1995-05-15), pages 936-943, XP004066766 ISSN: 0925-9635 page 937, paragraph 2; figure 1 page 938, paragraph 4 -----	1,2, 5-12,14, 15
A	VOEVODIN A A ET AL: "Design of a Ti/TiC/DLC functionally gradient coating based on studies of structural transitions in Ti-C thin films" THIN SOLID FILMS, ELSEVIER-SEQUOIA S.A. LAUSANNE, CH, vol. 298, no. 1-2, 20 April 1997 (1997-04-20), pages 107-115, XP004125924 ISSN: 0040-6090 page 109; figure 3; table 1 page 110; figures 4,5 page 113; figure 9 -----	1,2,6, 8-10,15

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP2004/051320

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
DE 10018143	A	25-10-2001	DE 10018143 A1	25-10-2001
			AU 2844001 A	30-10-2001
			BR 0017216 A	10-06-2003
			WO 0179585 A1	25-10-2001
			EP 1272683 A1	08-01-2003
			EP 1362931 A1	19-11-2003
			JP 2004501793 T	22-01-2004
			US 2004038033 A1	26-02-2004
			US 6740393 B1	25-05-2004
US 6126793	A	03-10-2000	JP 3304320 B2	22-07-2002
			JP 2000080474 A	21-03-2000
			JP 2997215 B2	11-01-2000
			JP 10081969 A	31-03-1998
			US 6033533 A	07-03-2000
			US 6217952 B1	17-04-2001
US 6033533	A	07-03-2000	JP 3304320 B2	22-07-2002
			JP 2000080474 A	21-03-2000
			JP 2997215 B2	11-01-2000
			JP 10081969 A	31-03-1998
			US 6217952 B1	17-04-2001
			US 6126793 A	03-10-2000